

Pro Tour Golf Sand

TYPICAL SIEVE ANALYSIS

US SIEVE	mm		Cum % Passing	Ind % Retained	USGA Greens Recommendation
#10	2.00	Gravel	100	-	≤ 10
#18	1.00	Very Coarse	93.0	7.0	
#35	0.50	Coarse	43.0	50.0	≥ 60%
#60	0.25	Medium	7.0	36.0	
#100	0.15	Fine	3.0	4.0	≤ 20
#270	0.05	Very Fine	0.5	2.5	≤ 5
PAN				0.5	

Particle Angularity:	Sub Angular - Angular
Particle Sphericity:	Medium
Bulk Density:	95 lbs/ft ³
Ksat:	> 40"/hr
Penetrometer Value:	≥ 2.2 kg/cm ²
Uniformity Coefficient	2.3
D15 (mm)	0.31
D50 (mm)	0.56
D85 (mm)	0.91

The information presented on this report lists typical properties of the described product. By this report P.W. Gillibrand Co., Inc. makes no warranty, expressed or implied, of fitness for any purpose. Values valid for 90 days.