



Typical Sieve Gradation

Location: Simi Valley
Product: Construction Grade

Date: 12/31/2024

US SIEVE	mm	in	Washed Concrete			Washed Plaster			Fill Sand		
			% Passing	Cum % Retained	Ind % Retained	% Passing	Cum % Retained	Ind % Retained	% Passing	Cum % Retained	Ind % Retained
3/8"	9.5	0.375	100	0	0				100	0	0
#4	4.8	0.187	97	3	3	100.0	0.0	0.0	99	1	1
#8	2.4	0.093	81	19	16	97.9	2.1	2.1	98	2	1
#16	1.2	0.046	70	30	11	84.2	15.8	13.7	96	4	3
#30	0.6	0.024	55	45	15	62.0	38.0	22.2	91	9	5
#50	0.3	0.012	31	69	24	27.1	72.9	34.9	81	19	10
#100	0.2	0.006	6	94	25	1.8	98.2	25.3	60	40	20
#200	0.1	0.003	0	100	6	0.1	99.9	1.7	24	76	36
PAN			0	100	0	0.0	100.0	0.1	0	100	24
Sand Equivalence				> 75			> 75			> 30	

Mineral: Feldspathic Gravel

Approximate Unit Weight: 90 lbs/cf

Shape: Sub Angular

Specific Gravity: 2.6

The information presented on this report lists typical properties of the described product. By this report P.W. Gillibrand Co., Inc. makes no warranty, expressed or implied, of fitness for any purpose. Values valid for 90 days.